

D7  
Can  
methyl(meth)acrylate-ethyl(meth)acrylate copolymers,  
ethyl(meth)acrylate-butyl(meth)acrylate copolymers, and (meth)-  
acrylate-styrene copolymers, said acrylic resin containing a  
lubricant in an amount to give a coefficient of kinetic friction  
with respect to a flat glass plate in the range of 0.2 to 0.9, said  
acrylic resin having a glass transition temperature of 80°C or  
below.

---

Cancel claim 15 without prejudice or disclaimer

Amend claim 16 as follows:

D2  
16. (Amended) The decorative sheet of claim 13, further  
comprising a backing resin sheet laminated to one surface of the  
decorative sheet.

---

Amend claim 17 as follows:

D3  
17. (Twice Amended) A sheet-decorated molding having a  
surface coated with a decorative sheet consisting essentially of an  
acrylic resin that is a member selected from the group consisting  
of polymethyl(meth)acrylate, polyethyl(meth)acrylate, poly-  
butyl(meth)acrylate, methyl(meth)acrylate-butyl (meth)acrylate

D3  
Cont

copolymers, methyl(meth)acrylate-ethyl(meth)acrylate copolymers, ethyl(meth)acrylate-butyl(meth)acrylate copolymers, and (meth)-acrylate-styrene copolymers, said acrylic resin containing a lubricant in an amount to give a coefficient of kinetic friction with respect to a flat glass plate in the range of 0.2 to 0.9, said acrylic resin having a glass transition temperature of 80°C or below.

---

Cancel claim 19 without prejudice or disclaimer.

Amend claims 20 and 21 as follows:

---

20. (Amended) The sheet-decorated molding of claim 17, further comprising a backing resin sheet interposed between the molding and the decorative sheet.

D4

21. (Amended) A decorative sheet for use in a sheet-decorating injection molding method, said decorative sheet consisting essentially of an acrylic resin selected from the group consisting of polymethyl(meth)acrylate, polyethyl(meth)acrylate, poly-butyl(meth)acrylate, methyl(meth)acrylate-butyl(meth)acrylate copolymers, methyl(meth)acrylate-ethyl(meth)acrylate copolymers,

*Def  
Cont* ethyl(meth)acrylate-butyl(meth)acrylate copolymers, and (meth)-  
acrylate-styrene copolymers, which contains a lubricant in an  
amount to give a coefficient of kinetic friction with respect to a  
flat glass plate in a range of 0.2 to 0.9.

---

ethyl(meth)acrylate-butyl(meth)acrylate copolymers, and (meth)-acrylate-styrene copolymers, which contains a lubricant in an amount to give a coefficient of kinetic friction with respect to a flat glass plate in a range of 0.2 to 0.9.